View NSN Online: https://aerobasegroup.gr/nsn/8040-01-363-3493

DEXTER AEROSPACE MATERIAL DIVISION -- EA 9323 5 GL SYSTEM, AS9110019 -- 8040-01-363-3493

Product ID:EA 9323 5 GL SYSTEM, AS9110019

MSDS Date:02/11/1993

FSC:8040

NIIN:01-363-3493

Kit Part:Y

MSDS Number: CDHFM === Responsible Party ===

Company Name: DEXTER AEROSPACE MATERIAL DIVISION

Address:2850 WILLOW PASS ROAD

Box:312

City:PITTSBURG

State:CA

ZIP:94565-0031

Countr v:US

Info Phone Num:510-458-8000

Emergency Phone Num:800-424-9300(CHEMTREC)

Preparer's Name: MSDS DEPT

CAGE:33564

=== Contractor Identification ===

Company Name: DEXTER CORPORATION ADHESIVE & COATING SYSTEMS

Address:2850 WILLOW PASS ROAD

Box:312

City:BAY POINT

State:CA

ZIP:94565-3299

Country:US

Phone:202-483-7616

CAGE:33564

Company Name: WATKINS AND ASSOCIATES INC

Address:5395 WEBB PKY

Box:City:LILBURN

State:GA ZIP:30047 Country:US

Phone:770-279-9200

CAGE:3D523

====== Composition/Informati

on on Ingredients =======

Ingred Name:4-GLYCIDYLOXY-N,N-DIGLYCIDYLANILINE

CAS:5026-74-4

Fraction by Wt: 30-60%

Other REC Limits: NONE RECOMMENDED

Ingred Name: DIGLYCIDYL ETHER OF BISPHENOL F

CAS:54208-63-8

Fraction by Wt: 10-30%

Other REC Limits: NONE RECOMMENDED

Ingred Name: POLYMER OF EPICHLOROHYDRIN, PHENOL-FORMALDEHYDE NOVOLAC

RESIN (ORAL RAT LD50 = >2000 MG/KG)

CAS:28064-14-4

Fraction by Wt: 10-30%

Other REC Limits: NONE RECOMMENDED

Ingred Name: VOC = 1LB UNLESS PLAN TO USE IMMED.D

ON'T

HEAT MIXED ADHESIVE >75F UNLESS CURING SURFACES TO BE BONDED.

====== Exposure Controls/Personal Protection ========

Respiratory Protection: UNNECESSARY WITH ADEQUATE EXHAUST VENTILATION.

Ventilation:LOCAL EXHAUST VENTILATION AT THE POINT OF USE.

Protective Gloves:BUTYL RUBBER, PVC, NITRILE RUBBER GLOVES

Eye Protection: SAFETY GLASSES W/SIDE SHIELD; CHEM GOGGLE

Other Protective Equipment: AN EYEWASH AND SAFETY SHOWER SHOULD BE NEARBY AND READY FOR USE.

Work Hygienic Prac

tices:WASH HANDS THOROUGHLY AFTER HANDLING MATERIALS.

Supplemental Safety and Health

FAILURE TO OBSERVE PRECAUTIONS IN MIXING/HEATING MAY RESULT IN EXCESSIVE HEAT BUILD-UP CAUSING AN EXOTHERM. THE EXOTHERM HAS POTENTIAL FOR RELEASE OF TOXIC GASES.

======== Physical/Chemical Properties ============

Boiling Pt:B.P. Text:UNDEFINED

Decomp Temp:Decomp Text:UNTESTED

Vapor Pres:0.001 Vapor Density:>1 Spec Gravity:1.19

Viscosity:*

Solubility in Water: NEGLIGIBLE.

Appearance an

d Odor:TAN PASTE, SLIGHT CHARACTERISTIC ODOR Corrosion Rate:NA

======== Stability and Reactivity Data =========

Stability Indicator/Materials to Avoid:YES

STRONG OXIDIZING AGENTS, STRONG LEWIS OR MINERAL ACIDS.

Stability Condition to Avoid: AVOID MIXING RESIN & CURING AGENT IN

BATCHES >1 LB. UNLESS YOU PLAN TO USE IMMEDIATELY, DON'T HEAT MIXED ADHESIVE >75F.

Hazardous Decomposition Products:CO, NOX, ALDEHYDES, ACIDS & UNDETERMINED ORGANICS.

Conditions to Avoid Pol

particular situation.

ymerization:POLYMERIZATION NOT LIKELY

======= Disposal Considerations ===========

Waste Disposal Methods:NOT RCRA HAZ WASTE.HOWEVER, INCINERATION IN EPA APPROVED WASTE INCINERATOR IS PREFERRED.CHEM ADDITIONS/ PROCESSING/OTHERWISE ALTERING MATL MAY MAKE WASTE MANAGEMENT INFOR HEREIN INCOMPLETE/INACCURATE/ INAPPROPRIATE.CONSULT STATE/LOC REGULATIONS.

Disclaimer (provided with this information by the compiling agencies):
This information is formulated fo
r use by elements of the Department
of Defense. The United States of America in no manner whatsoever,
expressly or implied, warrants this information to be accurate and
disclaims all liability for its use. Any person utilizing this
document should seek competent professional advice to verify and

assume responsibility for the suitability of this information to their